

Susceptibility magnetic and high magnetic field ESR measurement of $\text{SrCu}_2(\text{PO}_4)_2$

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=118312&lokasi=lokal>

Abstrak

The magnetic susceptibility and high magnetic ESR measurement of $\text{SrCu}_2(\text{PO}_4)_2$ has been performed at temperatures ranging from 4.2 K to 300 K and 4.2 K to 77 K, respectively. The magnetic susceptibility shows a broad maximum around $T = 40$ K. The magnetic susceptibility has been interpreted in terms of one-dimensional magnetic systems. The temperature dependence of the magnetic susceptibility indicated a good agreement with 4-spin alternating configuration model. In the ESR measurement, clear electron spin resonance (ESR) was observed. The integrated intensity for 120 and 301 GHz has a broad maximum at around 40 K, which is consistent with the susceptibility result. A quantitative description gives resonance is the first and second triplet excited states of the excitation spectrum of 4-spin alternating chain configuration. The g_1 , g_2 and g_3 values are approximately 2.21 at temperature above 40 K. The g_2 dan g_3 values have the dependence of temperature under 40 K.