

Sintesis dan karakterisasi N Doped TiO₂ (N/TiO₂) nanotube serta uji aktivitas fotokatalisis terhadap zat warna rhodamin B = Synthesis and characterization of N doped TiO₂ (N/TiO₂) nanotubes and photocatalytic activity test toward rhodamine B

Ida Nur Apriani, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=20433982&lokasi=lokal>

Abstrak

Telah dilakukan sintesis fotokatalis N/TiO₂ bermorfologi nanotubes dengan ammonium nitrat sebagai sumber dopan dengan cara metode anodisasi dan karakterisasinya menggunakan XRD, SEM-EDX, DRS UV-Vis serta pengujian yaitu Linear Sweep Voltametri dan Multi Pulse Amperiometri serta. Fotokatalis N/TiO₂ telah berhasil diterapkan untuk degradasi senyawa Rhodamin B menggunakan sinar UV maupun sinar tampak. Sintesis N/TiO₂ nanotube (N/TiO₂- NT) dilakukan dengan metode anodisasi dengan ammonium nitrat (NH₄NO₃) sebagai sumber dopan pada berbagai variasi konsentrasi (0,5M , 1M, 2M), dilanjutkan dengan kalisisasi pada suhu 4500C selama 2 jam untuk mendapatkan fasa kristal anatase. Karakterisasi dengan FTIR terhadap N/TiO₂ hasil masil sintesis memberikan puncak spektra FTIR Ti-O-Ti (700-800 cm⁻¹), Ti-N (450-500 cm⁻¹) dan O-N-O (1360 dan 1500 cm⁻¹), dan karakterisasi dengan spektrum Energy Dispersive Xray (EDX) menunjukkan keberadaan unsur N.

Hasil kedua karakterisasi tersebut mengindikasikan tersisipnya unsur nitrogen kedalam matrik TiO₂. Karakterisasi dengan UV-Vis DRS menunjukkan adanya sedikit penurunan energi celah pada N/TiO₂ (2,98 eV) dibandingkan TiO₂ yang tidak didoping (3,18 eV). Hasil pengukuran photocurrent menunjukkan bahwa N/TiO₂-NT aktif pada daerah visible, sedangkan TiO₂ nanotube tanpa dopan hanya aktif pada daerah UV. Dari uji fotokatalisis menggunakan sinar tampak diperoleh bahwa N/TiO₂-NT mempunyai aktifitas fotokatalis yang lebih baik daripada TiO₂ nanotube tanpa dopan dalam mendegradasi Rhodamkin B. Uji fotoelektrokatalisis menggunakan sinar tampak untuk N/TiO₂-NT memberikan hasil eliminasi sebesar 47,86%, sedangkan bila menggunakan TiO₂ nanotube tanpa dopan eleminasi hanya sebesar 25,49%. Hasil-hasil diatas menunjukkan bahwa proses doping yang dilakukan telah berhasil menyisipkan nitrogen kedalam matrik TiO₂ nanotubes dan memperbaiki kinerja fotokatalisis nya di daerah sinar tampak.

.....Synthesize and characterization of nitrogen doped TiO₂ (N/TiO₂) photocatalysts having nanotube morphology has been done by anodization method, with ammonium nitrate as a dopant source.

Characterization of prepared photocatalysts were conducted by XRD, SEM-EDX, UV-Vis Diffused Reflectant Spectrometry (UV-Vis DRS). Photoelectrochemical Test for photocurrent evolution examination was conducted by mean Linear Sweep Voltammetry and Multi pulse Amperometry. The prepared N/TiO₂ photocatalysts then was applied to a photocatalytic elimination of rhodamine B under illumination of UV and visible light. The N/TiO₂ nanotubes (N/TiO₂-NT) synthesis was performed by anodization method, with ammonium nitrate (NH₄NO₃) solution as a dopant at various concentration (0,5 M , 1 M, and 2 M), and followed by calcination at 4500C for 2 hours, to obtain anatase crystalline phase. FTIR characterization of prepared N/TiO₂-NT showed some peaks related to -Ti-O-Ti- vibration (700-800 cm⁻¹), -Ti-N vibration (450-500 cm⁻¹) and -O-NO- vibration (1360 and 1500 cm⁻¹). The EDX characterization clearly indicates the presence of nitrogen peak.

Both FTIR and EDX characterization indicated that the insertion of nitrogen into the TiO₂ matrix.

Characterization by UV-Vis DRS showed a slight decrease in the energy gap at N/TiO₂ (2.98 eV) compared to that undoped TiO₂ (3.18 eV). The results of photocurrent measurements showed that the N/ TiO₂-NT was active in the visible region, while the undoped TiO₂ nanotube was only active in the UV region. Photocatalytic testing toward Rhodamin B solution showed that, under visible light illumintaion, the N/TiO₂-NT photocatalyst perfomed better than that of undoped TiO₂ nanotube. Unde visible light, at certain time course, the N/TiO₂-NT can eliminate as much 47,86% Rhodamine B, while undoped TiO₂ nanotubes can only eliminate 25,49%. The results indicate that the doping treatment have been successfully inserting the nitrogen into the matrix of TiO₂ nanotubes and improve the performance of its photocatalytic property under visible light region.