

# Green Synthesis Nanokomposit ZnO/LaFeO<sub>3</sub> dengan Ekstrak Daun Mangkokan (*Nothopanax Scutellarium*) dalam Sistem Dua Fasa dan Aktivitas Fotokatalitiknya terhadap Malasit Hijau = Green Synthesis of ZnO/LaFeO<sub>3</sub> Nanocomposites using *Nothopanax Scutellarium* Leaf Extract in Two Phases System and Its Photocatalytic Activity of Malachite Green

Khabibil Mustofa, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=20494098&lokasi=lokal>

---

## Abstrak

<p style="text-align: justify;"><em>Green synthesis </em>nanopartikel ZnO, nanopartikel LaFeO<sub>3</sub>, dan nanokomposit ZnO/LaFeO<sub>3</sub> berhasil dilakukan menggunakan ekstrak daun mangkokan (<em>Nothopanax Scutellarium</em>) dalam sistem dua fasa dengan metode pengadukan kecepatan tinggi. Senyawa metabolit sekunder yaitu alkaloid digunakan sebagai agen penghidrolisa (sumber basa lemah –OH), sedangkan saponin dan steroid digunakan sebagai agen penstabil (<em>capping agent</em>). Hasil sintesis selanjutnya dikarakterisasi menggunakan instrumentasi spektrofotometer UV-Vis, UV-Vis DRS, spektroskopi FTIR, XRD, PSA, SEM-EDX, dan TEM. Difraktogram nanokomposit ZnO/LaFeO<sub>3 </sub>memiliki gabungan nilai difraksi  $2\hat{l}$ , dari nanopartikel ZnO dan LaFeO<sub>3 </sub>yang menunjukkan bahwa tidak terbentuk struktur yang baru. Hasil karakterisasi UV-Vis DRS menunjukkan bahwa nanopartikel ZnO, nanopartikel LaFeO<sub>3</sub>, dan nanokomposit ZnO/LaFeO<sub>3</sub> memiliki nilai <em>band gap</em> berturut-turut 3,1 eV; 2,25 eV; dan 2,05 eV. Aktivitas fotodegradasi nanokomposit ZnO/LaFeO<sub>3</sub> terhadap malasit hijau lebih baik daripada nanopartikel ZnO dan LaFeO<sub>3-</sub> dengan persentase berturut-turut sebesar 95,61%; 90,03%; dan 87,58% dibawah sinar tampak selama 2 jam penirangan. Kinetika fotodegradasi malasit hijau menggunakan nanokomposit ZnO/LaFeO<sub>3</sub> mengikuti reaksi sorde satu semu.</p><p> </p><hr /><p style="text-align: justify;">Green synthesis of ZnO nanoparticle, LaFeO<sub>3 </sub>nanoparticle, and ZnO/LaFeO<sub>3</sub> nanocomposites have been done by *Nothopanax Scutellarium* leaf in two phases system with high speed stirring method. Alkaloid, a secondary metabolite compound, is used as hydrolysis agent (base source -OH) and saponin is used as capping agent. Next, synthesized product is characterized by UV-Vis spectrophotometer instrumentation, UV-Vis DRS spectrophotometer, FTIR spectroscopy, XRD, PSA, SEM-EDX, and TEM. Diffractogram ZnO/LaFeO<sub>3 </sub>composites have a combined diffraction value at  $2\hat{l}$ , from ZnO and LaFeO<sub>3 </sub>nanoarticles and show that they don't create a new structure. UV-Vis DRS characterized product shows that ZnO nanoparticle, LaFeO<sub>3</sub> nanoparticle, and ZnO/LaFeO<sub>3</sub> nanocomposites have band gap value at 3,1 eV; 2,25 eV; and 2,05 eV, respectively. Photodegradation activity of malachite green using ZnO/LaFeO<sub>3</sub> nanocomposites is better than ZnO and LaFeO<sub>3-</sub> nanoparticles under visible light for 2 hours of radiation. Degradation percentage of malachite green using ZnO/LaFeO<sub>3</sub> nanocomposites is better than ZnO and LaFeO<sub>3-</sub>nanoparticles for about 95,61%; 90,03%; and 87,58%, respectively. Photodegradation kinetics of malachite green using ZnO/LaFeO<sub>3 </sub>nanocomposites follows pseudo first order reaction.</p><p> </p>