

Pengaruh proses leaching pada roasted slag feronikel dengan variasi 6 dan 8 m asam klorida sebagai agen pelindi terhadap recovery magnesium = Effect of leaching process on roasted slag ferronickel with variation 6 and 8 m hydrochloric acid as leaching agent against magnesium recovery.

Jordan Andrean Martin, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=20505271&lokasi=lokal>

Abstrak

Paduan Feronikel (*FeNi*) merupakan salah satu produk utama yang dihasilkan dalam pengolahan bijih nikel laterit. Negara Indonesia merupakan salah satu negara dengan deposit nikel besar dalam bentuk bijih laterit. Penelitian ini bertujuan untuk meningkatkan kadar senyawa Magnesium melalui proses *leaching* menggunakan larutan asam klorida dengan variasi konsentrasi larutan dan waktu proses *leaching*. Sampel yang digunakan berupa *Slag Feronikel* yang telah diberikan penambahan aditif Na_{2}CO_3 dan telah dipanggang dengan temperatur 1100°C . Penelitian dilakukan dengan melakukan proses *leaching* sampel menggunakan larutan HCl 4M dan 6M. Proses *leaching* untuk setiap konsentrasi larutan kemudian divariasikan waktu proses *leaching* yang digunakan yaitu 2, 4, dan 6 Jam. Setelah proses *leaching* mencapai waktu yang ditentukan, dilakukan proses penyaringan untuk memisahkan filtrat dan residu yang dihasilkan. Pada filtrat hasil *leaching* dilakukan karakterisasi ICP-OES untuk mengidentifikasi unsur-unsur yang terlarut pada filtrat selama proses *leaching* berlangsung. Sedangkan residu hasil *leaching* dilakukan karakterisasi SEM/EDS untuk mengetahui perubahan yang terjadi pada residu setelah proses *leaching*. Hasil dari penelitian ini menunjukkan bahwa adanya peningkatan kadar Magnesium dari kadar sebelum dilakukan proses *leaching*. Proses *leaching* menggunakan larutan HCl 6M menghasilkan peningkatan kadar Magnesium yang lebih besar. Selain itu, waktu proses *leaching* yang digunakan juga berpengaruh terhadap hasil yang dilakukan, dimana proses *leaching* Roasted Slag *Feronikel* memiliki waktu optimal untuk proses ekstraksi senyawa Magnesium. Berdasarkan hasil penelitian ini, dapat disimpulkan bahwa larutan asam klorida (HCl) yang digunakan dalam proses *leaching* Roasted Slag *Feronikel* dapat meningkatkan kadar senyawa Magnesium pada filtrat. Proses *leaching* yang paling optimal pada penelitian ini menggunakan larutan HCl 6M selama 4 Jam, dengan persentase *leaching* sebesar 49,05%.

<hr>

Feronickel Alloy (*FeNi*) is one of the main products produced in the processing of nickel laterite ore. Indonesia is one of the countries with a large nickel deposit in the form of laterite ore. This research aims to increase the levels of Magnesium compounds through the leaching process using hydrochloric acid solutions with varying solution concentrations and leaching process times. The sample used is the Feronickel Slag which has been given the addition of the Na_2CO_3 additive and has been baked at an 1100°C temperature. Research is conducted by conducting leaching process samples using a solution of HCl 4M and 6M. The leaching process for each solution concentration is then varied when the leaching process used are 2, 4, and 6 hours. After the leaching process reaches the specified time, the

filtering process is performed to separate the filtrate and the resulting residue. In filtrate, leaching is performed ICP-OES characterization to identify the dissolved elements of the filtrate during the progress of the leaching process. Meanwhile, leaching residue is performed SEM/EDS characterization to know the changes occurring in residue after leaching process. The results of this study showed that the presence of increased levels of Magnesium from levels prior to leaching processes. The leaching process using a 6M HCl solution produces a greater increase in Magnesium levels. In addition, the leaching process time used also affects the results, where the leaching process of Roasted Slag Feronickel has the optimal time for the extraction process of Magnesium compounds. Based on the results of this study, it can be concluded that a solution of hydrochloric acid (HCl) used in the leaching process of Roasted Slag Feronikel can increase the levels of Magnesium compounds in filtrate. The most optimal leaching process in this study was using an 6M HCl solution for 4 hours, with a leaching percentage of 49,05%.