

# Green Synthesis Nanomaterial Ga<sub>2</sub>O<sub>3</sub> via Ekstrak Daun Pepaya Jepang (Cnidoscolus aconitifolius) dalam Berbagai Pelarut: Sifat Optik, Struktur, Morfologi, dan Aktivitas Fotokatalitik = Green Synthesis of Ga<sub>2</sub>O<sub>3</sub> Nanomaterial via Cnidoscolus aconitifolius Leaf Extract in Various Solvents: Optical, Structural, Morphological, and Photocatalytic Activity

Vatra Reksa Ananda, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=9999920518311&lokasi=lokal>

---

## Abstrak

Dalam penelitian ini, green synthesis nanomaterial  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-M}$ ,  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$ , dan  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  via ekstrak daun Cnidoscolus aconitifolius telah berhasil dilakukan. Nanomaterial  $\hat{I}^2\text{-Ga}_2\text{O}_3$  dianalisis dengan karakterisasi XRD (X-ray Diffraction), UV-Vis DRS (UV-Vis Diffuse Reflectance Spectroscopy), FTIR (Fourier Transform Infrared), SEM (Scanning Electron Microscopy), EDS (Energy Dispersive X-ray Spectroscopy), dan TEM (Transmission Electron Microscopy). Hasil karakterisasi XRD menunjukkan bahwa sistem kristal  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-M}$ ,  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$ , dan  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  adalah monoklinik dengan grup ruang C12/m1 fasa tunggal. Pengukuran FTIR mengonfirmasi struktur kristal  $\hat{I}^2\text{-Ga}_2\text{O}_3$  berupa serapan karakteristik di 662 cm<sup>-1</sup> dan 431 cm<sup>-1</sup>. Spektroskopi UV-Vis DRS menunjukkan sifat optik  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-M}$ ,  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$ , dan  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  berupa serapan foton di daerah sinar UV dengan bandgap sebesar 4,59 eV, 4,66 eV, dan 4,61 eV, secara berurutan. Karakterisasi SEM-EDS menunjukkan bahwa  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-M}$ ,  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$ , dan  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  memiliki morfologi irregular shape, submicroblock, dan microspindle serta komposisi unsur penyusun yang sesuai secara stoikiometri. Karakterisasi TEM menunjukkan ukuran partikel rata-rata material  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-M}$ ,  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$ , dan  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  sebesar  $38,18 \pm 6,58$  nm,  $865,85 \pm 165,98$  nm, dan  $2926,01 \pm 331,26$  nm. Aktivitas fotokatalitik  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-M}$ ,  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$ , dan  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  pada proses fotodegradasi metilen biru adalah sebesar  $92,64 \pm 0,45$  %,  $20,07 \pm 0,97$  %, dan  $86,70 \pm 0,04$  %, secara berurutan. Kinetika reaksi fotokatalisis  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-M}$  mengikuti model reaksi orde nol dengan tetapan laju sebesar  $4,1 \times 10^{-3}$  M·menit<sup>-1</sup> serta  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$  dan  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  mengikuti model reaksi orde satu semu dengan tetapan laju sebesar  $1,6 \times 10^{-3}$  menit<sup>-1</sup> dan  $1,64 \times 10^{-2}$  menit<sup>-1</sup>, secara berurutan.

.....In this research, green synthesis of  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-M}$ ,  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$ , and  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  nanomaterials via Cnidoscolus aconitifolius leaf extract has been successfully carried out.  $\hat{I}^2\text{-Ga}_2\text{O}_3$  nanomaterials are characterized by XRD (X-ray Diffraction), UV-Vis DRS (UV-Vis Diffuse Reflectance Spectroscopy), FTIR (Fourier Transform Infrared), SEM (Scanning Electron Microscopy), EDS (Energy Dispersive X-ray Spectroscopy), and TEM (Transmission Electron Microscopy). XRD characterization results showed that  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-M}$ ,  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$ , and  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  are single phased and adopted monoclinic crystal system with C12/m1 space group. FTIR measurement confirmed the  $\hat{I}^2\text{-Ga}_2\text{O}_3$  crystal structure, which showed characteristic absorption in 662 cm<sup>-1</sup> and 431 cm<sup>-1</sup>. UV-Vis DRS spectroscopy showed optical properties of  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-M}$ ,  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$ , and  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  which absorbs photon in UV region with bandgap value of 4,59 eV, 4,66 eV, and 4,61 eV, respectively. SEM-EDS results showed that morphological shape of  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-M}$ ,  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$ , and  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  are irregular shape, submicroblock, and microspindle, also elemental composition that corresponds stoichiometrically. TEM characterization results showed that  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-M}$ ,  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$ , and  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  have average particle size of  $38,18 \pm 6,58$  nm,  $865,85 \pm 165,98$

nm, and  $2926,01 \pm 331,26$  nm. Photocatalytic activity of  $\hat{I}^2\text{-Ga}_2\text{O}_{<3}\text{-M}$ ,  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$ , and  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  in methylene blue photodegradation are  $92,64 \pm 0,45$  %,  $20,07 \pm 0,97$  %, dan  $86,70 \pm 0,04$  %, respectively. Photocatalysis kinetics of  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-M}$  followed the zeroth order reaction model with rate constant of  $4,1 \times 10^{-3}\text{M}\cdot\text{min}^{-1}$  while  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-Hx}$  and  $\hat{I}^2\text{-Ga}_2\text{O}_3\text{-W}$  followed the pseudo first order reaction model with rate constant value of  $1,6 \times 10^{-3} \text{ min}^{-1}$  and  $1,64 \times 10^{-2} \text{ min}^{-1}$ , respectively.